



FAA ALLOWABLE¹

NORBOND™ 220-0133-500

Upper Skin Material Thickness	One Ply 7781 Style E-Glass / Epoxy Resin 0.010 inch
Lower Skin Material Thickness	One Ply 7781 Style E-Glass / Epoxy Resin 0.010 inch
Core Material	Nomex® Honeycomb
Density	1/8 inch cell size; 3.0 lb/ft ³ ; Aramid Fiber Paper

² Panel Property	Test Results Value		Failure Mode	Tested IAW	
Max Weight, lb/ft ²	0.353		---	---	
Typical Weight, lb/ft ²	0.327		---	---	
Thickness, inch	0.500 ± 0.010		---	ASTM C 366	
³ Warpage, inch	0.025 max		---	---	
Long Beam Flexure	A-Basis	B-Basis	Upper Skin Compression	ASTM C 393 ASTM D 7249	
	"L" Direction Skin Stress, psi	26,568			29,140
	"L" Direction P/Y, lb/in	110			119
	"W" Direction Skin Stress, psi	21,896			24,750
	"W" Direction P/Y, lb/in	93			97
Short Beam Shear			Core Shear	ASTM C 393	
	"L" Direction Stress, psi	136			144
	"W" Direction Stress, psi	78			91
Stabilized Core Compression, psi	250	282	Core Crush	ASTM C 365	
Climbing Drum Peel, in-lb/3-inch width	Minimum		Cohesive	ASTM D 1781	
	15				

1/ 8110-3 available on request.

2/ Panel meets FAR 25.853a, 60 second vertical burn requirements.

3/ Panel warpage is measured as a maximum deviation from a straight line in a 4 foot span.

NOTICE: All data and statements concerning this product are based upon FAA witnessed testing by NORDAM under controlled conditions. This information, therefore, may be considered as being indicative of representative properties and characteristics obtainable. **This data has been FAA DER witnessed.** We make no warranty, expressed or implied, concerning its use, nor do we accept responsibility for any misapplications of this product, or its use under any conditions.